




HOW TO CALCULATE THE ENERGY EFFICIENCY OF YOUR LIME BURNING PROCESS


Introduction

The practice of burning limestone to produce quicklime is, almost literally, as old as the hills. In terms of basic chemistry and materials, the process involves the conversion of calcium carbonate, CaCO_3 , to the more useful calcium oxide, CaO . Calcium oxide is a very reactive substance. In fact, it is so 'lively' that it is usually hydrated (has water added) to form calcium hydroxide, Ca(OH)_2 . Calcium hydroxide is commonly called hydrated or slaked lime, and sometimes merely lime - which can be confusing as powdered limestone is often referred to in the same way. Hydrated lime is a more convenient material to handle and use than quicklime. Quicklime and hydrated lime have a very wide - and well documented - variety of uses.

This conversion of calcium carbonate to calcium oxide is achieved by heating the limestone to a temperature high enough (e.g. 1000°C in a lime kiln) to 'drive off' carbon dioxide, CO_2 . The equation for this process, with the approximate molecular weights, is:



Continuing the approximation for hydration gives:



So, in simple terms, if the process were carried out with 1 tonne of limestone which was pure calcium carbonate, it should produce 560 kg of quicklime. And if 180 kg (approximately 180 litres) of water were added to this quicklime, then 740 kg of calcium hydroxide should result.

Types of limestone

Calcite is a limestone which contains only calcium carbonate, CaCO_3 . There are other types of limestone which are of interest. Dolomite has the chemical formula $\text{CaCO}_3.\text{MgCO}_3$, i.e. it is a 'mixture' of calcium and magnesium carbonates in the proportion 1:1 of their molecules. Dolomitic limestones are those which contain some proportion of dolomite. Similarly, quicklime and hydrated lime may contain oxides and hydroxides of magnesium as well as of calcium.

technical brief



Some limestones are dolomitic, that is they contain the mineral dolomite, $\text{CaCO}_3\text{MgCO}_3$, in addition to the CaCO_3 which is present as the mineral calcite. Usually, pure calcitic limestones are preferable but dolomite can be tolerated provided the quicklime is well slaked before use.

Figure 1: A traditional lime kiln in Sudan. Photo: Simon Croxton / Practical Action

Efficiency of lime burning

Lime burners are generally seeking to produce the highest quality quicklime possible from their stone whilst keeping their production costs to a minimum. In the majority of cases, a very major production cost will be the fuel used. Thus, the efficiency of the burning process (as opposed to the whole process of production which will involve labour costs etc.) is judged by how much fuel it takes to produce a quantity of quicklime. For instance, a lime-burner may say “I produced *X* tonnes of quicklime using *Y* tonnes of coal which cost me *Z* dollars”. However, in order to compare different types of kilns using various fuels and producing quicklime of variable quality, it is necessary to develop a more universal measure of efficiency.

Kiln or burning efficiency can be determined and compared using the formula for thermal efficiency proposed by Robert Boynton, former director of the National Lime Association in the USA, in his book ‘Chemistry and Technology of Lime and Limestone’:



Figure 2: An improved vertical shaft kiln in Zimbabwe. Photo: Kelvin Mason / Practical Action.

$$\text{Thermal efficiency (\%)} = \frac{\text{theoretical heat requirement} \times \text{available oxide content(\%)}}{\text{total heat requirement}}$$

technical brief

This can be presented mathematically by the efficiency equation:

$$E = \frac{H_c \times L_s}{C_f \times M_f}$$

Where

- E = Efficiency of the burning process
- H_c = Theoretical heat of calcination per tonne for pure quicklime, CaO plus MgO (MJ/tonne)
- L_s = Available lime content (as CaO and MgO) of the quicklime
- C_f = Calorific value of fuel (MJ/kg)
- M_f = Mass of fuel used per tonne of quicklime (kg/tonne)

NB: Take care when using this formula that the units used are as specified or, if different units are used, that mathematical consistency is maintained.

Explanation and derivation of terms

H_c

For all practical purposes, this can be taken as 3,200 MJ/tonne CaO for a pure calcite limestone. For a pure dolomite limestone the figure is lower at 3,020 MJ. It is reasonably straight forward to adjust the figure for 'dolomitic' limestones as follows in the example.

From a test on limestone the following chemical analysis was obtained:

Table 1: Chemical analysis obtained on limestone (%)	
Silicon oxide, SiO ₂	2.03%
Aluminium Oxide, Al ₂ O ₃	0.67%
Iron Oxide, Fe ₂ O ₃	0.33%
Calcium Oxide, CaO	45.50%
Magnesium Oxide MgO	8.16%
Sulphuric Anhydride, SO ₃	0.39%
LOI (at 1,000°C)	42.40%

A test on the quicklime produced the following result:

Table 2: Chemical analysis obtained on limestone (%)	
Silicon oxide, SiO ₂	2.34%,
Aluminium Oxide, Al ₂ O ₃	0.63,
Iron Oxide, Fe ₂ O ₃	0.35%,
Calcium Oxide, CaO	68.40%,
Magnesium Oxide MgO	17.8%,
Sulphuric Anhydride, SO ₃	0.25%,
LOI (at 1,000°C)	9.80%

H_c is obtained by calculating the energy required to calcine the calcitic fraction of the limestone and that required to calcine the dolomitic fraction, and adding these two figures.

For the limestone in our example, the calcium oxide and magnesium oxide values (45.50% and 8.16% respectively) indicate the stone has 60.95% calcite and 37.32% dolomite. These values are obtained using the molecular weights of CaO, MgO, CaCO₃ and MgCO₃.^(Table 3)

Thus,

$$H_c = (3200 \times 0.6095) + (3020 \times 0.3732) = 3,078 \text{ MJ}$$

Calculating the proportions of calcite and dolomite

Based on the chemical analysis of the limestone in our example (i.e. calcium oxide, CaO = 45.50% and magnesium oxide, MgO = 8.16%), this calculation assumes that all the calcium and magnesium is present as carbonates - whereas, a small, and probably insignificant, amount may occur as silicates etc. Firstly, we determine the amount of dolomite, CaCO₃.MgCO₃, from the amount of MgO present in our stone compared with the percentage in 100% dolomite.

$$\text{MgO in pure dolomite} = \frac{40.32}{184.42} \times 100 = 21.86\%$$

An MgO content of 8.16% means the amount of dolomite is calculated thus:

$$\text{dolomite in stone} = \frac{8.16}{21.86} \times 100 = 37.32\%$$

Now we determine the percentage of the CaO that would be taken up by this amount of dolomite:

$$37.32 \times \frac{56.08}{184.42} = 11.35\%$$

Then we subtract this from the total CaO to obtain the amount that is taken up as CaCO₃, i.e. calcite:

$$45.50 - 11.35 = 34.15\%$$

The proportion of CaCO₃ as calcite in the limestone is thence given by:

$$34.15 \times \frac{100.09}{56.08} = 60.95\%$$

Thus the approximate carbonates content of our limestone is 61% calcite and 37% dolomite. As these amount to a little over 98% and the chemical analysis has other constituents, silica etc., which amount to 3.42%, then the amount of the total carbonate can be expected to be somewhat lower, say 96 to 97%

Ls

The available lime content, as CaO and MgO, of quicklime is obtained from the Rapid Sugar Test^(Figure 1). This test should be performed *immediately* the quicklime is withdrawn from the kiln. This is because, being very reactive, the quicklime is very prone to carbonation and, if the test is delayed, a lower value for Ls is likely. A value of Ls could also be obtained by performing the Rapid Sugar Test on the calcium hydroxide but the value obtained is likely to be lower, and thus invalidate any calculation of burning efficiency. For the purpose of our example we will assume Ls = 0.60^(Table 4)

Cf

The calorific value of fuel is obtained using a calorimeter. A university department or a commercial laboratory will probably have the appropriate facilities, i.e. a bomb calorimeter. If this facility is unavailable, then a general value may be taken for a particular fuel^(Table 4). For the purpose of our example, we will assume we have a bituminous coal with a calorific value of 23 MJ/kg^(Table 5).

Figure 1: American Society of Testing Materials ASTM Rapid Sugar Test (using hydrochloric acid)

Apparatus

- 300ml Erlenmeyer flask (a conical flask having contents volume marked on it).
- 100ml burette with stand.
- Balance capable of weighing 0.85g and 0.5g to an accuracy of 2%.
- No.100 mesh sieve (0.15mm). CO₂ - free distilled water if available.
- Hydrochloric acid (specific gravity 1.18).
- Methyl orange indicator.
- Phenolphthalein indicator.
- 15g of sucrose (granulated sugar is satisfactory).

Method

This procedure enables a semi-direct reading of the available CaO to be obtained. It is important to ensure that the sample is exposed as little as possible to the atmosphere during preparation and storage.

- Prepare a standard HCl solution which has 15.7ml of HCl (specific gravity 1.18) per litre of CO₂ - free distilled water. The solution is standardised against 0.85g of anhydrous Na₂CO₃ with methyl orange as indicator so that this amount will neutralise exactly 90ml of standard HCl solution. In adjusting for this, add more water if it is too strong or more acid if too weak.
- Take 0.5g of lime which has been passed through a 100 mesh, brush it into the 300ml flask containing 20ml of CO₂ - free distilled water, and stopper the flask. Swirl and heat to boiling for two minutes. Add 150ml of water and at least 15g of sucrose. Stopper the flask and shake at intervals for 5 minutes. Allow to stand for 30 to 60 minutes. Add two drops of phenolphthalein, wash down stopper and sides of flask with more distilled water then titrate in the original flask with the standard HCl solution. Add about 90% of the estimated amount of the acid before shaking the flask and then complete titration with the final acid being fed slowly until the pink colour disappears. Note the reading.

Calculation

A 1ml reading on the burette gives an available CaO of 1%.

Mf

The mass of fuel used per tonne of quicklime produced must be carefully recorded in the field over a set period of time. It is relatively easy to obtain a figure if limestone is burned using a batch process. However, if a continuous or semi-continuous process is used, then care must be taken that the mass of fuel used and the mass of quicklime produced correspond directly. In our example, we will take a figure for the coal used as 200 kg/tonne of quicklime produced.

technical brief

calcite, CaCO ₃	100.09
dolomite, CaCO ₃ . MgCO ₃	184.42
calcium oxide, CaO	56.08
magnesium oxide, MgO	40.32

A more precise calculation of the fraction of calcite limestone CaCO₃, and any dolomite CaCO₃.MgCO₃, converted to CaO and CaO + MgO, is complex and involves using these molecular weights.

Fuel	Calorific value (MJ/kg)
Commercial Butane	58
Diesel fuel	44
Heavy fuel oil	42
Charcoal (2% moisture)	29
Anthracite coal	33
General purpose coal (non-coking)	23
Wood (15% moisture)	15

MJ/kg	cals/gram	Btu/lb	kWh/tonne
1	239	430	278

Example of efficiency calculation

Having obtained values for all the terms in the equation we can now calculate efficiency:

$$E = \frac{H_c \times L_s}{C_f \times M_f}$$

$$E = \frac{3078 \times 0.60}{23 \times 200}$$

$$E = 0.4015$$

$$E = 0.40 \text{ or } 40\%$$

It is obvious from the formula, and indeed from the application of common sense, that for maximum efficiency lime-burners should aim for maximum conversion of calcium carbonate to calcium oxide while using the minimum quantity of fuel. However, minimising fuel use without evaluating the quality of the lime produced can give a very false impression of efficiency.

An indication of a target efficiency using, for example, a forced draught vertical shaft kiln, is 50%. In terms of monitoring the performance of any lime burning process, it is evident from the above example that the essential information to collect and calculate is: a chemical analysis of the limestone, a value for theoretical heat of calcination (H_c) based on molecular weights, a value for the available lime content (L_s) obtained from the Rapid Sugar Test, the calorific value of fuel (C_f) and the mass of fuel per tonne of quicklime produced (M_f).

Conclusion

In developing this methodology Practical Action seeks to ensure that various kiln designs and operational practices can be optimised in terms of energy usage and ultimately production costs. This approach is by no means offered as definitive or untouchable; indeed it is designed to encourage debate.

References and further reading

- [Alternatives to Portland Cement](#) Practical Action Technical Brief
- [Lime - An Introduction](#) Practical Action Technical Brief
- [Hydraulic Lime - An Introduction](#) Practical Action Technical Brief
- [Methods for testing lime in the field](#) Practical Action Technical Brief
- [How to Build a Small Vertical Shaft Lime Kiln](#) Practical Action Technical Brief
- [A Small Lime Kiln for Batch and Continuous Firing](#) Practical Action Technical Brief
- [Pozzolanas - An Introduction](#) Practical Action Technical Brief
- [Small Scale Production of Lime for Building](#) John Spiropoulos, GTZ, 1985
- [Gypsum Plaster: Its Manufacture and Use](#), A. Coburn, E. Dudley and R. Spence, Practical Action Publishing, 1989
- [Small-scale Lime-burning: A practical introduction](#) Michael Wingate, Practical Action Publishing, 1985
- [The Small Scale Vertical Shaft Lime Kiln: A practical guide to design, construction and operation](#), Kelvin Mason, Practical Action Publishing, 1999
- [Building with Lime: A practical introduction. Revised Edition](#) Stafford Holmes & Michael Wingate, Practical Action Publishing, 2002/3
- [A Case Study in Lime Production: Improved design of a lime kiln in Sri Lanka](#), Practical Action Technical Brief
- [Lime Production: Traditional batch techniques in Chenkumbi](#), Practical Action Technical Brief
- [A Case Study in Lime Production No2 Improved Techniques at Chenkumbi, Malawi](#), Practical Action Technical Brief
- [Lime Production: A traditional kiln at Bou Noura, Algeria](#), Practical Action Technical Brief
- [Lime Production: Traditional batch techniques in Patará, Costa Rica](#), Practical Action Technical Brief
- [Lime and Alternative Binders in East Africa](#), Elijah Agevi et al, Practical Action /ODA, 1995
- [Lime and Other Alternative Cements](#) Neville Hill et al, Practical Action Publishing, 1992
- [Limes for Building](#), Advisory Leaflet No.6, Property Services Agency, Department of the Environment, HMSO, London, 5th Edn., 1976.
- [The Chemistry of Cement and Concrete](#), Lea, P.M., Edward Arnold, London, 3rd Edn. 1970.
- [Lime and Lime Mortars](#), A.D. Cowper, Building Research Special Report No.9, His Majesty's Stationary Office, London, 1927 (republished 1998 by Donhead Publishing, Shaftesbury, Dorset, England).
- [Supplementary Cementing Materials for Use in Blended Cements](#), R.J. Detwiler, J.I. Bhatti, S. Bhattacharja, Research and Development Bulletin RD112T, Portland Cement Association, Skokie, Illinois, USA, 1996

This technical brief was prepared by Neville Hill and Kelvin Mason for World Cement 1997. Special thanks are due to Barrie Evans and Michael Wingate for their comments and editorial assistance in compiling this article.

Practical Action
The Schumacher Centre
Bourton-on-Dunsmore
Warwickshire, CV23 9QZ
United Kingdom
Tel: +44 (0)1926 634400
Fax: +44 (0)1926 634401
E-mail: inforserv@practicalaction.org.uk
Website: <http://practicalaction.org/practicalanswers/>

This Technical Brief is an output from a project funded by the UK Overseas Development Administration (ODA) for the benefit of developing countries. The views expressed are not necessarily those of the ODA. The Technical Brief was made available electronically with the assistance of The Tony Bullard Trust.

Practical Action is a development charity with a difference. We know the simplest ideas can have the most profound, life-changing effect on poor people across the world. For over 40 years, we have been working closely with some of the world's poorest people - using simple technology to fight poverty and transform their lives for the better. We currently work in 15 countries in Africa, South Asia and Latin America.

technical brief